

VDM® Powder CoCr F75

VDM® Powder CoCr F75

VDM® Powder CoCr F75 is a non-magnetic cobalt-chrome-molybdenum-based superalloy for use in additive manufacturing.

VDM® Powder CoCr F75 is characterized by:

- Spherical particles
- High purity
- Low oxygen content
- Good corrosion and temperature resistance
- Excellent wear resistance

Designations

Standard	Material designation
ISO	5832-12 / 5832-4
ASTM	F1537-11 / F75
UNS	R31538 / R30075

Table 1 – Designations

Chemical composition

	Co	Cr	Mo	Ni	Fe	C	Si	Mn	W	P	S	N	Al	Ti	B
Min.	bal- ance	27.0	5.0												
Max.		30.0	7.0	0.50	0.75	0.35	1.0	1.0	0.20	0.020	0.010	0.25	0.10	0.10	0.010

Table 2 – Chemical composition (%) according to ASTM F75

VDM® Powder CoCr F75 contains low amounts of oxygen of up to 0.03 %.

Physical properties

Density8.3 g/cm³ at 20 °C (68 °F)

Melting range1,350-1,430 °C (2,462-2,606 °F)

Corrosion resistance

As a result of the high chromium content, VDM® Powder CoCr F75 has very good general corrosion and temperature resistance.

Applications

Due to its good corrosion, temperature and wear resistance, VDM® Powder CoCr F75 is intended for the use as medical prosthetic implant like knee implants, metal-to-metal hip joints or dental prosthetics. Furthermore, it is appropriate for high-temperature engineering applications like aero- and land-based gas turbines as gas nozzles and vanes for industrial gas turbines.


Availability

According to the AM process requirements of our customers, VDM® Powder CoCr F75 is available in a wide range of particle fractions from 15 to 250 µm.

Standard particle fractions

Particle size distribution µm	Oxygen content %	Porosity > 20µm ² (pore area) %
15-53	< 0.03	< 0.5
53-150		

Additional particle fractions are available on request. Please contact us.



The picture shows a typical micrograph of VDM® Powder CoCr F75 as an example.

Legal notice

May 15, 2020

Publisher

VDM Metals International GmbH
Plettenberger Straße 2
58791 Werdohl
Germany

Disclaimer

All information contained in this data sheet is based on the results of research and development work carried out by VDM Metals International GmbH and the data contained in the specifications and standards listed available at the time of printing. The information does not represent a guarantee of specific properties. VDM Metals reserves the right to change information without notice. All information contained in this data sheet is compiled to the best of our knowledge and is provided without liability. Deliveries and services are subject exclusively to the relevant contractual conditions and the General Terms and Conditions issued by VDM Metals International GmbH. Use of the most up-to-date version of this data sheet is the responsibility of the customer.

VDM Metals International GmbH
Plettenberger Strasse 2
58791 Werdohl
Germany

Phone +49 (0)2392 55 0
Fax +49 (0)2392 55 22 17
vdm@vdm-metals.com
www.vdm-metals.com